

via Roma 76,
23895 Bulciago (LC) - Italy
info@jacqart.com
jacqart.com

TECHNICAL SHEET

Quality : RUSSOLO	Design : 15/621/A	
Composition	%	34% L I 20% W O 14% M I 12% P PL 11% C CO 9% P PA
Finishing		A
Weight	gr/mtl	785 ±5%
Useable width	cm	140
Horizontal repeat	cm	/
Vertical repeat	cm	/
Abrasion resistance EN ISO 12947-2 (Martindale method)	cycles	>100. 000
Abrasion resistance ASTM D4157 (Wyzenbeek method)	doublerubs	
Pilling test EN ISO 12945-2 (Martindale method)	grade	3/ 4
Seam Slippage EN ISO 1936-2	warpways (mm) weftways (mm)	5 5
Breaking Strength EN ISO 13934-1	warpways (N) weftways (N)	
Tear Strength EN ISO 13937-3	AcrossWarp(N) AcrossWeft(N)	
Colour Fastness to Light EN ISO 105 : B02	grade	5
Colour Fastness to Rubbing EN ISO 105-X12	dry (grade) wet (grade)	4/ 5 4
Colour Fastness to Water EN ISO 105 : E01	staining (grade) change col. (grade)	
Technical Bulletin 117-2013	results	PASS
Cigarette test (BS 5852 : 2006 – Source 0)	results	PASS
Match test (BS 5852 : 2006 – Source 1)		
Dimensional stability to washing		
Horizontal	%	
Vertical	%	
Cleaning instructions	    	